



GENERAL FASTNESS AND PROPERTIES

| | | | | |
|---|---|--|---|--|
| P E N E T R A T I O N | L I G H T F A S T | P E R S P I R A T I O N F A S T | W A S H I N G F A S T | M I G R A T I O N I N P V C |
|---|---|--|---|--|

| 3% | 4% | | | | | | |
|----|----|-------------------------|-----|-----|-----|-----|-----|
| | | ARC COLOR YELLOW S | 3 | 3 | 4 | 4 | 4 |
| | | ARC COLOR YELLOW L | 3 | 3 | 4 | 4 | 4 |
| | | ARC COLOR YELLOW R | 3-4 | 4 | 4 | 4-5 | 4 |
| | | ARC COLOR BROWN P | 3-4 | 4 | 2-3 | 2-3 | 4 |
| | | ARC COLOR BROWN NTE | 4 | 4 | 3 | 2-3 | 4 |
| | | ARC COLOR BROWN RS | 4-5 | 3-4 | 3 | 2 | 4-5 |
| | | ARC COLOR BROWN MFR | 4-5 | 4 | 3 | 2-3 | 3 |
| | | ARC COLOR BROWN NRE | 4-5 | 3 | 4 | 2-3 | 4-5 |
| | | ARC COLOR BROWN GR | 4 | 5 | 3 | 3 | 3 |
| | | ARC COLOR OLIVE BROWN S | 4-5 | 4 | 3-4 | 3 | 4-5 |



GENERAL FASTNESS AND PROPERTIES

| | | | | |
|---|--|---|--|--|
| P E N E T R A T I O N | L I G H T F S T | P E R S P I R A T I O N F S T | W A S H I N G F S T | M I G R A T I O N I N P V C |
|---|--|---|--|--|

| 3% | 4% | | | | | | |
|----|----|-----------------------|-----|-----|-----|-----|-----|
| | | ARC COLOR BEIGE G | 4 | 3-4 | 3 | 4 | 4 |
| | | ARC COLOR BEIGE S | 4 | 3-4 | 3 | 4 | 4 |
| | | ARC COLOR BORDEAUX | 2-3 | 3 | 2-3 | 3-4 | 4-5 |
| | | ARC COLOR BROWN RD | 4-5 | 3 | 3 | 2-3 | 3 |
| | | ARC COLOR TOBACCO | 3 | 3 | 3-4 | 4 | 4 |
| | | ARC COLOR HAVANA S | 3-4 | 4 | 3-4 | 4-5 | 3 |
| | | ARC COLOR GREEN S | 4-5 | 3-4 | 3-4 | 4-5 | 4 |
| | | ARC COLOR BLUE EXS | 5 | 4 | 4 | 4 | 4 |
| | | ARC COLOR VIOLET | 4 | 1 | 3-4 | 4 | 4 |
| | | ARC COLOR BRIGHT BLUE | 2-3 | 3 | 2-3 | 3-4 | 4-5 |



GENERAL FASTNESS AND PROPERTIES

| | | GENERAL FASTNESS AND PROPERTIES | | | | | |
|----|----|---|---|--|---|--|--|
| | | | P E N E T R A T I O N | L I G H T F S T | P E R S P I R A T I O N F S T | W A S H I N G F S T | M I G R A T I O N I N P V C |
| 3% | 4% | | | | | | |
| | | ARC COLOR GREY S | 3 | 5 | 4 | 4 | 4-5 |
| | | ARC COLOR GREY SX | 3-4 | 2-3 | 3 | 3 | 2-3 |
| | | ARC COLOR ORANGE GS | 3-4 | 4 | 3-4 | 3-4 | 3-4 |
| | | ARC COLOR RED S | 3 | 2-3 | 4 | 3 | 3 |
| | | ARC COLOR RED SX | 3 | 2-3 | 3-4 | 3-4 | 3 |
| | | ARC COLOR BLACK EXS (A. BLACK 210 STD) | 4 | 4-5 | 4 | 4 | 4 |
| | | ARC COLOR BLACK EXSX (A. BLACK 234 STD) | 4 | 5 | 4-5 | 3-4 | 4-5 |
| | | ARC COLOR BLACK EXC (A. BLACK 234 CRUDE) | 4 | 5 | 4-5 | 4 | 4-5 |
| | | ARC COLOR BLACK EXTRA (A. BLACK 210 CRUDE) | 4 | 4-5 | 4 | 4 | 4 |
| | | ARC COLOR BLACK EXSL (A. BLACK 210 -150%) | 4 | 4-5 | 4 | 4 | 4 |